

# TEST REPORT

**APPLICANT** : ZHEJIANG JIAJIA RIDE-ON CO.,LTD

**ADDRESS** : INDUSTRY PARK OF XINCANG, PINGHU, ZHEJIANG,  
CHINA

**SAMPLE DESCRIPTION** : CHILDREN'S CAR

**ITEM NO.** : JE1818、JE1001

**AGE REQUESTED ON APPLICATION FORM** : 37-96 Months

**LABELED AGE GRADE** : 37-96 Months

**AGE GRADE APPLIED IN TESTING** : 37-96 Months

**SAMPLE RECEIVED DATE** : 04-Jun-2020

**TURN AROUND TIME** : 04-Jun-2020 to 12-Jun-2020

The following test item(s) was/were performed on selected sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Mechanical and Physical Properties	ASTM F963-17	A,B :Pass
Flammability of Toys	ASTM F963-17	A,B :Pass
Heavy Metals	ASTM F963-17	A,B :Pass
Total Lead Content in Paint / Surface Coating	US CPSIA, Section 101	Pass
Total Lead Content in Substrate	US CPSIA, Section 101	Pass
Phthalates Content	US CPSIA, Section 108	Pass
Phthalates Content	CPSC 16 CFR part 1307	Pass

*Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to [info.sh@eurofins.com](mailto:info.sh@eurofins.com) and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to [chinacomplaint@eurofins.com](mailto:chinacomplaint@eurofins.com) and*

\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*


Signed for and on behalf of  
Eurofins Product Testing Service (Shanghai) Co., Ltd



---

Joyce Liu  
Lab Manager

## TEST SAMPLE PHOTO(S)



# EFSH20060454-CG-01

\*\*\*TO BE CONTINUED\*\*\*

## **REFERENCE SAMPLE PHOTO(S)**



The reference sample(s) has not been tested in current report, but according to customer's request, the picture has also been included. For sample tested in current report, please refer to "Test sample photo".

# **EFSH20060454-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

## COMPONENT LIST

Component No.	Component	Sample No.
1	White coating on plastic	A
2	Silver coating on plastic	A
3	White soft plastic wire jacket	A
4	Black soft plastic wire jacket	A
5	Red soft plastic wire jacket	A
6	Blue soft plastic wire jacket	A
7	Orange soft plastic wire jacket	A
8	Transparent soft plastic (gear)	B
9	Blue plastic body	A
10	Black plastic body	A B
11	Transparent red plastic (button/lamp)	A B
12	Transparent orange plastic (lamp)	B
13	Grey plastic excluding coating	A
14	White plastic excluding coating (steering wheel)	A
15	Transparent black plastic (windshield)	B
16	White plastic (tongue)	A
17	Black plastic button	A
18	Black plastic seat	A
19	Transparent plastic (lamp)	A
20	Blue plastic (logo)	A
21	White plastic (logo)	A
22	Black plastic (logo)	A
23	Dark blue plastic (logo base)	A
24	Pink plastic	C
25	Red plastic (remote control)	A B
26	Ivory plastic (remote control)	A B
27	Black plastic (remote control)	A B
28	Black fabric (safetybelt)	A
29	Silver plated metal (logo)	A
30	Silver metal screw (remote control)	A B

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Mechanical and Physical Properties

Test Request: As specified in Consumer Safety Specification ASTM F963-17

Section	Description	Result
4.1	Material Quality	P
4.3.7	Stuffing Materials	N/A
4.5	Sound-Producing Toys	P
4.6	Small Objects	N/A
4.6.1	Toys that are intended for children under 36 months of age	N/A
4.6.2	Mouth-Actuated Toys	N/A
4.6.3	Toys that are intended for children over 36 months but less than 72 months	N/A
4.7	Accessible Edges	P
4.8	Projections	P
4.8.1	Bath Toy Projections	N/A
4.9	Accessible Points	P
4.10	Wires or Rods	P
4.11	Nails and Fasteners	P
4.12	Plastic Film	P
4.13	Folding Mechanisms and Hinges	P
4.14	Cords, Straps and Elastics	N/A
4.15	Stability and Over-Load Requirements	P
4.16	Confined Spaces	N/A
4.17	Wheels, Tires, and Axles	P
4.18	Holes, Clearances, and Accessibility of Mechanisms	P
4.19	Simulated Protective Devices	N/A
4.20	Pacifiers	N/A
4.21	Projectile Toys	N/A
4.22	Teethers and Teething Toys	N/A
4.23	Rattles	N/A
4.24	Squeeze Toys	N/A
4.25	Battery-Operated Toys (exclude section 4.25.10 Battery-powered ride-on toys and section 4.25.11 Toys contain secondary cells or secondary batteries)	P
4.26	Toys Intended to be Attached to a Crib or Playpen	N/A
4.27	Stuffed and Beanbag-Type Toys	N/A
4.28	Stroller and Carriage Toys	N/A
4.30	Toy Gun Marking	N/A
4.31	Balloons	N/A
4.32	Certain Toys with Nearly Spherical Ends	N/A
4.33	Marbles	N/A
4.34	Balls	N/A
4.35	Pompoms	N/A
4.36	Hemispheric-Shaped Objects	N/A
4.37	Yo Yo Elastic Tether Toys	N/A
4.38	Magnets	N/A
4.39	Jaw Entrapment in Handles and Steering Wheels	N/A
4.40	Expanding material	N/A
4.41	Toy Chests	N/A
5	Labeling Requirements	
5.2	Age Grading Labeling	P

## TEST RESULT

Section	Description	Result
5.3	Safety Labeling Requirements	P
5.4	Aquatic Toys	N/A
5.5	Crib and Playpen Toys	N/A
5.6	Mobiles	N/A
5.7	Stroller and Carriage Toys	N/A
5.8	Toys Intended to be Assembled by an Adult	P
5.9	Simulated Protective Devices	N/A
5.10	Toys with Functional Sharp Edges and Sharp Points	N/A
5.11	Small Objects, Small Balls, Marbles and Balloons (16 CFR 1500.19)	N/A
5.12	Toy Caps (16 CFR 1500.86 for Required Labeling)	N/A
5.13	Art Materials (16 CFR 1500.14(b)(8))	N/A
5.14	Electric Toys	N/A
5.15	Battery-Operated Toys	P
5.15.1	Battery-Powered Ride-On Toys	P
5.15.2	Button or Coin Cell Batteries	N/A
5.16	Promotional Materials	N/A
5.17	Magnets	N/A
6	Instructional Literature	
6.1	Definition and Description	P
6.2	Crib and Playpen Toys	N/A
6.3	Mobiles	N/A
6.4	Toys Intended to be Assembled by an Adult	P
6.5	Battery-Operated Toys	P
6.6	Battery-Powered Ride-On Toys	P
6.7	Toys in Contact with Food	N/A
6.8	Toy Chests	N/A
7	Producer's Markings	
7.1	Producer's or Distributor's Name and Address	P
7.2	Battery-Powered Ride-on Toys	P
7.3	Toy Chests	N/A

**Remark:**

P – Pass

N/A – Not Applicable

\*\*\*TO BE CONTINUED\*\*\*

## **TEST RESULT**

### **Flammability of Toys**

Test Request: As specified in ASTM F963-17, Section 4.2, testing procedure for materials other than textiles (excluding paper) used in toys is contained in Annex A5.

Sample	Limit	Result
A	0.1 inch/second	P
B	0.1 inch/second	P

**Remark:**

P – Pass

\*\*\*TO BE CONTINUED\*\*\*



## TEST RESULT

### Heavy Metals

1) ASTM F963-17- Heavy Elements – Total Lead in Paint and Similar Surface-Coating Material(Clause 4.3.5.1(1))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result	
				1	2
Total Lead	mg/kg	90	10	ND	ND

2) ASTM F963-17- Heavy Elements – Total Lead in Substrate Material (Clause 4.3.5.2(2)(a))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				3	4	5	6	7
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				8	9	10	11	12
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				13	14	15	16	17
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				18	19	20	21	22
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				23	24	25	26	27
Total Lead	mg/kg	100	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				29			30	
Total Lead	mg/kg	100	10	ND			ND	

3) ASTM F963-17- Heavy Elements – Total Elements Content, Initial Screening for Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay(Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.1 and Annex A7.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4	5
Total Antimony	mg/kg	60	5	ND	ND	ND	37	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	ND	ND	ND	ND	25
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Tested Item(s)	Unit	Limit	MDL	Result				
				6	7	8	9	10
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	ND	36	ND	ND	54
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				11	12	13	14	15
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	21	59	13	ND	14
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				16	17	18	19	20
Total Antimony	mg/kg	60	5	ND	212*	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	136	ND	12	57	ND
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result				
				21	22	23	24	25
Total Antimony	mg/kg	60	5	ND	ND	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND	ND	ND
Total Barium	mg/kg	1000	10	44	ND	41	ND	84
Total Cadmium	mg/kg	75	5	ND	ND	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND	ND	ND
Total Mercury	mg/kg	60	5	ND	ND	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND	ND	ND

\*\*\*TO BE CONTINUED\*\*\*

Tested Item(s)	Unit	Limit	MDL	Result		
				26	27	28
Total Antimony	mg/kg	60	5	ND	ND	ND
Total Arsenic	mg/kg	25	5	ND	ND	ND
Total Barium	mg/kg	1000	10	49	ND	ND
Total Cadmium	mg/kg	75	5	ND	ND	ND
Total Chromium	mg/kg	60	5	ND	ND	ND
Total Lead	mg/kg	90	10	ND	ND	ND

## TEST RESULT

Total Mercury	mg/kg	60	5	ND	ND	ND
Total Selenium	mg/kg	500	10	ND	ND	ND

4) ASTM F963-17- Heavy Elements – Soluble Migrated Elements Content in Surface Coatings and Substrates Other Than Modeling Clay (Clause 4.3.5.1(2) and 4.3.5.2(2)(b))

Test Method: ASTM International Standard ASTM F963-17, Section 8.3.2 to 8.3.5 (excluding 8.3.5.5(3))

Tested Item(s)	Unit	Limit	MDL	Result
				17
Soluble Antimony	mg/kg	60	5	ND
Soluble Arsenic	mg/kg	25	5	ND
Soluble Barium	mg/kg	1000	10	ND
Soluble Cadmium	mg/kg	75	5	ND
Soluble Chromium	mg/kg	60	5	ND
Soluble Lead	mg/kg	90	10	ND
Soluble Mercury	mg/kg	60	5	ND
Soluble Selenium	mg/kg	500	10	ND

### Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

The analytical results were adjusted by subtracting analytical correction factor.

\* On the initial analysis for soluble heavy metals content, any tested component of greater than the set limit, the result is inconclusive for the requirement and therefore were retested with soluble heavy metals analysis of ASTM F963-17, Sections 8.3.2 to 8.3.5 as specified in Section 8.3.1.3. The result herein is for reference only (show data), please refer to soluble heavy metals content analysis for the corresponding conclusive results.  
As per client's request, only the appointed materials have been tested.

\*\*\*TO BE CONTINUED\*\*\*

## **TEST RESULT**

### **Total Lead Content in Paint / Surface Coating**

Test Request: Total lead in paint/ similar surface coatings as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1003-09.1  
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result
				1+2
Total Lead(Pb)	mg/kg	90	10	ND

**Remark:**

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Total Lead Content in Substrate

Test Request: Total lead in substrate as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 101

Test Method: CPSC-CH-E1001-08.3, CPSC-CH-E1002-08.3  
The sample was acid digested, and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result			
				3+4+5	6+7+8	9+10+11	12+13+14
Total Lead(Pb)	mg/kg	100	10	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result			
				15+16+17	18+19+20	21+22+23	24+25+26
Total Lead(Pb)	mg/kg	100	10	ND	ND	ND	ND

Tested Item(s)	Unit	Limit	MDL	Result		
				27	29	30
Total Lead(Pb)	mg/kg	100	10	ND	ND	ND

**Remark:**

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

\*\*\*END OF THE REPORT\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Phthalates Content as specified in US Consumer Product Safety Improvement Act 2008 (CPSIA), Section 108

Test Method: CPSC-CH-C1001-09.4

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					3+4+5	6+7+8	9+10+11
For toys and childcare articles							
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children							
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					12+13+14	15+16+17	18+19+20
For toys and childcare articles							
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children							
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					21+22+23	24+25+26	27
For toys and childcare articles							
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Additional requirements for toys and childcare articles, which can be placed in the mouth by children							
Diisononyl phthalate (DINP)	68515-48-0	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND

### Remark:

MDL = method detection limit

ND = Not detected, less than MDL

## **TEST RESULT**

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Phthalates Content

Test Request: Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates as specified in CPSC 16 CFR part 1307.

Test Method: CPSC-CH-C1001-09.4

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					3+4+5	6+7+8	9+10+11
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					12+13+14	15+16+17	18+19+20
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					21+22+23	24+25+26	27
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DPENP)	131-18-0	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DHEXP)	84-75-3	%	0.1	0.005	ND	ND	ND
Dicyclohexyl phthalate (DCHP)	84-61-7	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND

### Remark:



## **TEST RESULT**

MDL = method detection limit

ND = Not detected, less than MDL

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

As per client's request, only the appointed materials have been tested.

\*\*\*END OF THE REPORT\*\*\*