

TEST REPORT

Number : WUXH00125060

Applicant : ZHEJIANG JIAJIA RIDE-ON CO.,LTD
XINCANG INDUSTRIAL ZONE PINGHU CITY,
ZHEJIANG,CHINA.

Date : Jan 18, 2022

Sample Description:

One(1) Group Of Submitted Sample Said To Be :
Item Name : Children's Car.
Item No. : JE1001.
Labelled Age Group : For 37-96 months.
Packaging Provided By Applicant : Yes(Artwork).
Goods Exported To : EU.
Country Of Origin : China.

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(s).

Conclusion:

<u>Tested Sample</u>	<u>Standard</u>	<u>Result</u>
Submitted Sample	BS EN71-1 : 2014 + A1 : 2018 -Mechanical And Physical Properties	Pass
Submitted Sample	BS EN71-2: 2020 Flammability Test	Pass
Tested Components Of Submitted Sample	BS EN 71-3:2019+A1:2021 On Migration Of Certain Elements	Pass
Tested Components Of Submitted Sample	BS EN 71-3:2019+A1:2021 on migration of certain elements & (EU) 2019/1922 amending 2009/48/EC (effective from May,20 ,2020) for Aluminium (Al) migration	Pass

Prepared And Checked By:
For Intertek Testing Services Wuxi Ltd.



Peter Chen
General Manager



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

1 Mechanical and Physical Test

As Per European Standard on Safety of Toys BS EN71-1: 2014+ A1: 2018.

Applicant's Specified Age Group for Testing: For 37-96 months

The submitted samples were undergone the following abuse tests:

Test	Clause	Parameter
Torque Test	8.3	0.34 Nm
Tension Test	8.4.2.1	90 N
Protective Components	8.4.2.3	60 N
Drop Test	8.5	850 mm x 5times
Tip over test	8.6	Three times
Impact Test	8.7	1 kg
Compression Test	8.8	110 N

Clause	Testing Items	Assessment
4	General Requirements	
4.1	Material	P
4.2	Assembly	P
4.3	Flexible plastic sheeting	NA
4.4	Toy bags	NA
4.5	Glass	NA
4.6	Expanding materials	NA
4.7	Edges	P
4.8	Points and metallic wires	P
4.9	Protruding parts	P
4.10	Parts moving against each other	P
4.11	Mouth actuated toys and other toys intended to be put in the mouth	NA
4.12	Balloons	NA
4.13	Cords of toy kites and other flying toys	NA
4.14	Enclosures	NA
4.15	Toys intended to bear the mass of a child	P
4.16	Heavy immobile toys	NA
4.17	Projectile toys	NA
4.18	Aquatic toys and inflatable toys	NA
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	NA
4.20	Acoustics	P



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

Clause	Testing Items	Assessment
4.21	Toys containing a non-electrical heat source	NA
4.22	Small balls	NA
4.23	Magnets	NA
4.24	Yo-yo balls	NA
4.25	Toys attached to food	NA
4.26	Toy disguise costumes	NA
4.27	Flying toys	NA
5	Toys intended for Children under 36 Months	
5.1	General requirements	NA
5.2	Soft-filled toys and soft-filled parts of a toy	NA
5.3	Plastic sheeting	NA
5.4	Cords, chains and electrical cables in toys	NA
5.5	Liquid filled toys	NA
5.6	Speed limitation of electrically-driven ride-on toys	NA
5.7	Glass and porcelain	NA
5.8	Shape and size of certain toys	NA
5.9	Toys comprising monofilament fibres	NA
5.10	Small balls	NA
5.11	Play figures	NA
5.12	Hemispheric-shaped toys	NA
5.13	Suction cups	NA
5.14	Straps intended to be worn fully or partially around the neck	NA
5.15	Sledges with cords for pulling	NA
6	Packaging	NA
7	Warnings, markings and instructions for use	
7.1	General	P
7.2	Toys not intended for children under 36 months	P
7.3	Latex balloons	NA
7.4	Aquatic toys	NA
7.5	Functional toys	NA
7.6	Hazardous sharp functional edges and points	NA
7.7	Projectile toys	NA
7.8	Imitation protective masks and helmets	NA
7.9	Toy kites	NA
7.10	Roller skates, inline skates and skateboards and certain other ride-on toys	P
7.11	Toys intended to be strung across a cradle, cot, or perambulator	NA



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

Clause	Testing Items	Assessment
7.12	Liquid-filled teethingers	NA
7.13	Percussion caps specifically designed for use in toys	NA
7.14	Acoustics	NA
7.15	Toy bicycles	NA
7.16	Toys intended to bear the mass of a child	NA
7.17	Toys comprising monofilament fibres	NA
7.18	Toy scooters	NA
7.19	Rocking horses and similar toys	NA
7.20	Magnetic/electrical experimental sets	NA
7.21	Toys with electrical cables exceeding 300 mm in length	NA
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	NA
7.23	Toys intended to be attached to a cradle, cot or perambulator	NA
7.24	Sledges with cords for pulling	NA
7.25	Flying toys	NA
7.26	Improvised projectiles	NA

Remark: P = Pass NA = Not Applicable

Artwork of packaging was provided for testing.

Remark: Additional information according to the Toy Safety Directives 2009/48/EC requirement. These information also appears as a note within the EN 71 but are not standard requirements:

1. Marking

The manufacturer's and importer's name, registered trade name or registered trade mark, the address and the CE-marking shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompany the toy. In addition, manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.

After checking, it was found that:

	Toy	Packaging
Manufacturer's name	Absent	Present
Manufacturer's address	Absent	Present
Importer's name	Absent	Absent
Importer's address	Absent	Absent
Product identification code	Absent	Present
CE-marking	Absent	Absent

Below is additional information checking according to the UK Toy (Safety) Regulations requirement.

Marking



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

The manufacturer's and importer's name, registered trade name or registered trademark, the address and type, batch, serial or model number or other element allowing their identification shall be indicated on the product itself.

After checking, it was found that:

	Toy	Packaging
Name of authorised representative in Great Britain	Absent	Absent
Address of authorised representative in Great Britain	Absent	Absent
Product identification code	Absent	Present

With reference to the guidance of using UKCA marking from 1 January 2021 by the Department for Business, Energy and Industrial Strategy published on 1 September 2020.

After checking UKCA marking, it was found that:

	Toy	Packaging
UKCA marking	Absent	Absent

Date Sample Received: Dec 15, 2021

Testing Period: Dec 15, 2021 To Dec 30, 2021



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

2 Flammability Test

As per European Standard on Safety of Toys BS EN71-2: 2020

Clause	Testing Items	Assessment
4.1	General	P
4.2	Toys to be worn on the head	
4.2.2	Beards, moustaches, wigs, etc., made from pile or flowing elements which protrude 50 mm or more from the surface of the toy	NA
4.2.3	Beards, moustaches, wigs, etc., made from pile or flowing elements which protrude less than 50 mm from the surface of the toy	NA
4.2.4	Full or partial moulded head masks	NA
4.2.5	Toys to be worn on the head	NA
4.3	Toy Disguise Costumes and Toys Intended to be Worn by a Child in Play	NA
4.4	Toys Intended to be Entered by a Child	NA
4.5	Soft Filled Toys	NA

Remark : P = Pass NA = Not Applicable

Date Sample Received: Dec 15, 2021

Testing Period: Dec 15, 2021 To Dec 30, 2021



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

3 19 Toxic Elements Migration Test

(A) Test Result

As per BS EN 71-3:2019+A1:2021 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, and Gas Chromatographic - Mass Spectrometry.

Category (III): Scraped-off toy material

<u>Element</u>	<u>Result (mg/kg)</u>					<u>Limit (mg/kg)</u>
	(1)	(2)	(3)	(4)	(5)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Limit (mg/kg)
	(6)	(7)	(8)	(9)	(10)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Element	Result (mg/kg)					Limit (mg/kg)
	(11)	(12)	(13)	(14)	(15)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025#	< 0.025#	< 0.025	< 0.025#	< 0.025#	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	16	< 10	19	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0Δ	< 3.0Δ	< 3.0Δ	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Limit (mg/kg)
	(16)	(17)	(18)	(19)	(20)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025#	< 0.025#	< 0.025	< 0.025#	< 0.025#	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	11	18	11	18	12	180000
Organic tin ⁺⁺	< 3.0Δ	< 3.0Δ	< 3.0Δ	< 3.0Δ	< 3.0Δ	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Element	Result (mg/kg)					Limit (mg/kg)
	(21)	(22)	(23)	(24)	(25)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025#	< 0.025#	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	12	15	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0Δ	< 3.0Δ	< 3.0Δ	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

<u>Element</u>	<u>Result (mg/kg)</u>					<u>Limit (mg/kg)</u>
	(26)	(27)	(28)	(29)	(30)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

<u>Element</u>	<u>Result (mg/kg)</u>					<u>Limit (mg/kg)</u>
	(31)	(32)	(33)	(34)	(35)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025#	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

<u>Element</u>	<u>Result (mg/kg)</u>					<u>Limit (mg/kg)</u>
	(36)	(37)	(38)	(39)	(40)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025#	< 0.025	< 0.025#	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

<u>Element</u>	<u>Result (mg/kg)</u>					<u>Limit (mg/kg)</u>
	(41)	(42)	(43)	(44)	(45)	
Aluminium (Al)	< 300	< 300	< 300	< 300	331	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ⁺⁺	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ⁺⁺	< 0.025	< 0.025#	< 0.025	< 0.025	< 0.025#	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ⁺⁺	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

<u>Element</u>	<u>Result (mg/kg)</u>	<u>Limit (mg/kg)</u>
	(46)	
Aluminium (Al)	< 300	70000/28130◎
Antimony (Sb)	< 10	560
Arsenic (As)	< 10	47
Barium (Ba)	< 10	18750
Boron (B)	< 50	15000
Cadmium (Cd)	< 5	17
Chromium (III) (Cr III) ++	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025#	0.053
Cobalt (Co)	< 10	130
Copper (Cu)	< 10	7700
Lead (Pb)	< 10	23
Manganese (Mn)	< 10	15000
Mercury (Hg)	< 10	94
Nickel (Ni)	< 10	930
Selenium (Se)	< 10	460
Strontium (Sr)	< 100	56000
Tin (Sn)	< 10	180000
Organic tin ++	< 3.0	12
Zinc (Zn)	< 100	46000

Remark: mg/kg = Milligram per kilogram

++ = Unless the test results were marked with "#" or "Δ", Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.

- Organic tin test result was expressed as tributyl tin.
- Migration of Chromium (III) = Migration of total Chromium – Migration of Chromium(VI), when performed confirmation test for Chromium (VI)

◎ =)The new Aluminium (Al) migration limit [2250mg/kg for Category (I), 560mg/kg for Category (II), 28130mg/kg for Category (III)] was quoted from directive (EU) 2019/1922 amending 2009/48/EC effective from 20 May 2021.

= Confirmation of Chromium (VI) test was performed on the tested component. And the reported value of migration of Chromium (III) = migration value of total Chromium – migration value of Chromium(VI).

Δ = Confirmation test was performed on the tested component. The reported value was calculated by summation of the migration values of Methyl tin, Dibutyl tin, Tributyl tin, Tetrabutyl tin, n-Octyl tin, Di-n-octyl tin, Di-n-propyl tin, Diphenyl tin, Monobutyl tin and Triphenyl tin

Tested Component: See Component List In The Last Section Of This Report.



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

(B) Categories of various toy materials

Category I: Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II: Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III: Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).

Date Sample Received: Dec 15, 2021

Testing Period: Dec 15, 2021 To Jan 12, 2022




TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

Photo



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)



The Sample Were Submitted By Client's, Only For Reference.



TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)



Components List:

- (1) Purple Plastic(Body).
- (2) Yellow Plastic(Body).
- (3) Coffee Plastic(Body).
- (4) Pink Plastic(Body).
- (5) Grey Plastic(Body).
- (6) Blue Plastic(Body).
- (7) Deep Blue Plastic(Body).
- (8) Orange Plastic (Body).
- (9) White Plastic(Body).
- (10) Rice White Plastic(Body).
- (11) Green Plastic(Body).
- (12) Transparent Plastic(Body).
- (13) Coffee Soft Plastic (The Wire Skin).
- (14) Red Soft Plastic (The Wire Skin).
- (15) Deep Soft Plastic (The Wire Skin).
- (16) Green Soft Plastic (The Wire Skin).
- (17) Deep Green Soft Plastic (The Wire Skin).
- (18) Blue Soft Plastic (The Wire Skin).
- (19) Deep Blue Soft Plastic (The Wire Skin).
- (20) White Soft Plastic (The Wire Skin).
- (21) Black Soft Plastic (The Wire Skin).
- (22) Yellow Soft Plastic (The Wire Skin).

TEST REPORT

Number : WUXH00125060

Tests Conducted (As Requested By The Applicant)

- (23) Orange Soft Plastic (The Wire Skin).
- (24) Grey Coating On Plastic(Front Fence,Steering Wheel,gear Lever).
- (25) Dark Blue Plastic(Logo).
- (26) Coffee Transparent Plastic(Front Window).
- (27) Black Plastic(Front Fence).
- (28) Transparent Plastic(Front Light).
- (29) Red Transparent Plastic(Tail Light).
- (30) Black Plastic(Instrument Panel).
- (31) Transparent Soft Plastic With Black,White Printing(Button).
- (32) Black Plastic(Steering Wheel).
- (33) Black Plastic(Door).
- (34) Black Plastic(Seat).
- (35) Black Plastic(Safety Belt Adjuster).
- (36) Red Plastic(Safety Belt Adjuster).
- (37) Black Webbing(Safety Belt).
- (38) Black Plastic(Accelerator Pedal).
- (39) Black Soft Plastic(Wheel).
- (40) Black Plastic(Wheel Hub).
- (41) White Plastic(Coupling Of Wheel).
- (42) Beige Plastic(Coupling Of Wheel).
- (43) Grey Plastic(Front Chassis).
- (44) Light Grey Plastic(Tail Chassis).
- (45) White Adhesive Paper With Multi-Color Printing(Warning Label).
- (46) Black Coating On Metal(Chassis).

End of Report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band $w = U$) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) received and tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Wuxi Ltd.

